

## Colour Creation Formulations

### PanDOMO® Floor/Floor Plus and PanDOMO® Loft

Colour No.	Colour Formulation for 1kg of PanDOMO® K1 and K2
17/1.1	20g white*
17/1.2	without pigment*
17/1.3	0.1g black, 0.25g umber*
17/2.1	0.5g black, 0.1g red, 15g white*
17/2.2	1g black, 0.2g red
17/2.3	4g white, 5g black, 2.3g red
17/3.1	0.5g black, 0.75g umber
17/3.2	3.75g black
17/3.3	13.74g black
17/4.1	1.25g brown, 0.25g black, 0.05g red
17/4.2	5g oxide-ochre, 3g oxide red, 3g black
17/4.3	6g oxide-ochre, 5g oxide red, 9g black
17/5.1	0.1g black, 0.75g blue, 0.7g red
17/5.2	13g blue, 7g red
17/5.3	10g blue, 5g red, 5g black
17/6.1	0.5g black, 0.1g blue, 15g white*
17/6.2	1g black, 0.2g blue
17/6.3	5g white, 5g black, 2g blue
17/7.1	0.5g yellow, 0.5g blue, 15g red
17/7.2	2g red, 5g yellow
17/7.3	4.5g yellow, 1g green, 1.1g oxide-ochre, 0.1g black

\*PanDOMO® SP-PS Sealer is required for the completion of the PanDOMO® installation.

## Colour Creation Formulations

### PanDOMO® Wall W1

Colour No.	Colour Formulation for 1kg of PanDOMO® Wall
17/1.1	40g white*
17/1.2	without pigment*
17/1.3	0.2g black, 0.5g umber, 0.2g ochre
17/2.1	1g black, 0.2g red, 30g white*
17/2.2	2g black, 0.4g red
17/2.3	8g white, 10g black, 4.6g red
17/3.1	1g black, 1.5g umber
17/3.2	7.5g black
17/3.3	27.48g black
17/4.1	2.5g brown, 0.5g black, 0.1g red
17/4.2	10g oxide-ochre, 5g oxide red, 6g black
17/4.3	12g oxide-ochre, 9g oxide red, 17g black
17/5.1	0.2g black, 1.5g blue, 1.4g red
17/5.2	26g blue, 14g red
17/5.3	20g blue, 10g red, 10g black
17/6.1	1g black, 0.2g blue, 30g white*
17/6.2	2g black, 0.3g blue
17/6.3	10g white, 10g black, 4g blue
17/7.1	1g yellow, 1g blue, 30g red
17/7.2	4g red, 10g yellow
17/7.3	9g yellow, 2g green, 2.2g oxide-ochre, 0.2g black